
SEAL SPEC R03-R





description

as profile RO3-P but more adaptation possibilities for diverse temperatures and media by selection of suitable seal material.

category of profile

machined product only

double acting rotary shaft seal

the RO3-P seal is designed for use as a rotary shaft seal

operating parameter & material

material			tomporatura	max surface	max pressure ¹
sealing element	energizer	back-up ring	temperature	speed	max pressure.
NBR	-	POM / PA ²	-30 °C +100 °C	0,2 m/s	250 bar (25 MPa)
HNBR	-	POM / PA ²	-25 °C +100 °C	0,2 m/s	250 bar (25 MPa)
FKM	-	PTFE virgin	-20 °C +200 °C	0,2 m/s	250 bar (25 MPa)
FKM	-	PTFE glass	-20 °C +200 °C	0,2 m/s	250 bar (25 MPa)
FKM	-	PTFE bronze	-20 °C +200 °C	0,2 m/s	250 bar (25 MPa)
FKM	-	PTFE carbon	-20 °C +200 °C	0,2 m/s	250 bar (25 MPa)

¹ pressure ratings are dependent on the size of the extrusion gap

the stated operation conditions represent general indications. It is recommended not to use all maximum values simultaneously, surface speed limits apply only to the presence of adequate lubrication film.

surface quality


surface roughness	Rtmax (µm)	
sliding surface	≤3	≤0,3
bottom of groove	≤10	≤1,8
groove face	≤16	≤3

tolerance recommendation

seal housing tolerance				
Ød	h7			
ØD	H8			

seal & housing recommendations

please note that we are able to produce those profiles to your specific need or any non standard housing. for detail measurements, please see seal-mart catalog...





² POM up to ø260 mm, PA above ø260 mm